

MONNELI EPOFINISH F

Fairing Coat Solvent Free Epoxy Mortar (3mm or less)

Product Description

A solvent free, two components, easily workable epoxy mortar EPOFINISH F is based on a combination of epoxy resin and specially selected fillers.

It is suitable to fill and seal cavities and cracks in structural components, up to 3mm wide. It is also used for pin hole filling prior to application of epoxy coating.

Uses

EPOFINISH F is designed to provide repairs to surfaces in different situations, such as:

- Crack repairs in structural components, like bridges, industrial structures, columns, beams, foundations, walls and floors slabs
- Filling pinholes prior to over coating
- General re-profiling over large areas
- Dowel bars anchoring
- Bolt pocket, filling
- Used as adhesive to fix slip brick to concrete
- Repair surface defects on steel bridges bearings
- Used as bedding mortar for bridge beams or steel bridges bearing
- Used as mortar bedding in manhole chambers
- General re-profiling over large areas

Advantages

- Non shrink, solvent free product
- High mechanical strength, abrasion and impact resistance
- High chemical resistance against oils, greases, salt, petroleum and mild acids and alkalis, sewage, ammonia

- High corrosive resistance
- Excellent adhesive to concrete substrates
- Low viscosity, non-slump. Can be easily applied on vertical and overhead surfaces
- Pre-measured proportions, easy to mix and apply

Instructions for Use

Surface Preparation

The substrate must be clean, sound, free from grease, friable material, curing compound, etc. Dust should be removed by brush or compressed air.

All necessary repairs for wide cracks, degraded concrete, expansion joints, etc. should be made using one of the recommended range of concrete repair products before start to apply EPOFINISH F.

Mixing

Stir the hardener and base separately. Empty the hardener content into the base container and mix the two components thoroughly, till a uniform homogeneous paste is obtained. For perfect mixing, a low speed electric motor attached with a suitable paddle is recommended.

Application

Apply the mixed product using a trowel, scraper or filling knife. EPOFINISH F is a thixotropic workable product which makes it easier to obtain a smooth finished surface. Once the applied layer is cured, abrade slightly and clean from dust using compressed air before applying epoxy coating or finishing paint.

EPOFINISH F is designed to filling pin holes and to re-profiling and leveling irregularities in concrete surfaces prior to applying any epoxy coating system. Application thickness depends on substrate profile. The range of thickness will vary from feather edge up to a maximum of 3 mm.

Cleaning

Tools and equipment should be cleaned with SOLVENTE 10 immediately after use. Hardened material should be removed mechanically. Spillages should be absorbed with sand or sawdust and disposed of in accordance with local regulations.

Recommendations

- Do not use during rainy days or if temperature is less than +5°C.
- Application should not be carried out when atmosphere humidity exceeds 90%, or when the surface to be coated is less than +3°C above the dew point.

Technical Data

Properties	Results
Color	Light grey
Wet density at 25°C	1.65 kg/L
Solid content	100%
VOC	4.3 g/L
Pot life at 25°C	>60 minutes
Compressive strength at 7 days (ASTM C579)	>60 N / mm ²
Flexural strength (ASTM C 580)	18 N / mm ²
Tensile strength (BS6319 Pt. 7)	>20 N / mm ²
Over coating time	after 24 hours
Chemical resistance	Resistant to oils, bleach, fats, petrol, sea water, dilute mineral acids and solvents, sewage, urine, sulphur gases, ammonia.

All values are subject to 5-10 % tolerance

The information in this Technical Data Sheet is based on Colmef Monnelli's experience. Colmef Monnelli does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Colmef Monnelli's Data Sheets are updated on regular basis. It is the user's responsibility to obtain the latest version.

Consumption

0.61 m²/kg when applied at 1 mm thickness

Packaging

EPOFINISH F is supplied in 1kg and 5kg Kit

Storage

Store in original, unopened pack in covered, dry store. Avoid direct exposure to sunlight. Do not keep in stores with temperature less than +5°C or more than +30°C. It has a shelf life of 12 months if stored as recommended.

Health & Safety

During application, wear appropriate protective clothing, goggles, gloves and respiratory equipment if necessary.

In case of contact with skin, rinse with water and again wash thoroughly with soap and water. In case of contact with eyes, rinse with plenty of water and seek medical advice accordingly.

If ingested, obtain medical attention immediately. Do not induce vomiting.

DUBAI
ABU DHABI
ITALY

P.O. Box 123808 Dubai UAE
P.O. Box 127326 Abu Dhabi, UAE
Z.I. Ponte d'Assi 06024 Gubbio (PG)

T. +971 4 8803488 F. +971 4 8803450
T. +971 2 5511949 F. +971 2 5511749
T. +39 75 9221297 F. +39 75 9221174

colmef@colmef.ae

www.colmef-me.com

EPOFINISH F
Technical Data Sheet
Edition: January 2020
Revision: 02