

MONNELI INSUWRAP 2000 TNL-FB

2.0 mm thick Fleece-back PVC Membrane for Underground Structures & Tanking System

Product Description

Insuwrap 2000 TNL-FB is a homogeneous PVC (polyvinylchloride) sheet waterproofing membrane with a calendared geotextile layer on the back.

Uses

Insuwrap 2000 TNL-FB is used for:

- Waterproofing of basements, tunnels and other underground structures

Properties

Properties	Results
Appearance	PVC rolled sheet membrane
Membrane thickness	2.0 mm + Felt
Colour	White Colour

Advantages

- High tensile strength and elongation
- Hot air weldable
- Flexible throughout life span
- Resistant to ageing
- Long durability
- High dimensional stability
- Anti-Root membrane
- Can be installed on wet and dry substrates
- Designed to be used in hot climates
- Resistant to natural aggressive mediums in ground water soil
- Time and cost efficient
- Reduces the wrinkles in the geotextile layer
- Eliminates the risk of burning the geotextile under the PVC membrane during the welding process
- Minimize the risk of overlaps in geotextile

Standards

- Tested according to testing requirements of DIN 16938, DIN 16730, ASTM D3083 and SIA 280/10,11,12,15.

Technical Data

Test Performed	Test Method	Results
Membrane Thickness (mm)		2.0 + Felt
Tensile Strength Machine Direction Perpendicular Direction mpA	ASTM – D638 DIN 16730	≥16.0 N/mm ²
Elongation at Break (%)	ASTM – D638 DIN 16730	>300%
Tear Strength (N)	DIN 16730 80N (Min)	>100N
Thermal Stability	DIN 16730 90°C -6 hours Change less than 2%	<0.7%
Hardness Shore A (3 seconds)	ASTM D2240 78 DIN 16730	80±1
Cold bend	DIN 16730 No cracks at -20°C	No Cracks at -30 °C
Water Vapour diffusion resistance (μ)	DIN 16730 Less than 30,000	>21,000 μ
Tensile Strength Modulus Perpendicular (Psi)	ASTM D638 DIN 16730	1210 Psi
100% Modulus Machine Direction (Psi)	ASTM D638 DIN 16730	730
100 % Modulus Perpendicular Direction (Psi)	ASTM D638 DIN 16730	730
Specific Gravity	ASTM D792 DIN 16730	1.28
Compressive Strength	SIA V 280/14	Passed
Puncture Resistance	DIN 16730 Drop hammer 500 grams, no leak on falling from 300 mm	Passed
Impact Strength	DIN 16726/15.12	>800mm
Resistance to Algae & Rot	High resistance	High resistance

All values are subject to 5-10 % tolerance

Complimentary Products

- PVC Coated Aluminium sheet for termination
- Geotextile membrane
- Protection layer
- PU Sealant: Elastoseal PU
- Re-injectable hose: Elastojoint RHS
- Injection Resin: Betocryl 60
- Solvent base contact Adhesive: Neofil S10

Instruction for Use

Substrate Preparation

The surface of the concrete substrate shall be sound, clean, dry or wet, and uncontaminated. This preparation shall be as such as to leave a sound exposed concrete surface free from dust, laitance and any delirious matter.

The gunite surface must not contain broken aggregates. Any leaks shall be sealed with Murex, a water plug mortar, or with Betocryl 60, a Polyurethane injection resin. The surface of the gunite and fine sprayed concrete must be cleaned (no loose stones, nails, wires, etc.).

Application

PVC Fleece Back Sheet Installation (Fully Bonded System)

A. General: Install Fleece back sheets over entire area in full accordance with manufacturer's method statement.

1. Install membrane so that the PVC is at the visible side and the fleece back is towards the substrate.

B. Horizontal Installation:

1. Adhere the fleece back PVC membrane (fully bonded) using Neofil S10 adhesive to the entire horizontal area

2. Accurately align sheets and maintain uniform side and end laps of minimum dimensions required. Stagger end laps. B. Vertical Applications:

3. Install the Geotextile membrane as a protection layer over the entire area above the fleece back PVC membrane followed by a minimum of 50mm cementitious screed

C. Vertical Applications:

1. Adhere the fleece back PVC membrane (fully bonded) using Neofil S10 adhesive to the entire vertical area

2. Accurately align sheets and maintain uniform side and end laps of minimum dimensions required. Stagger end laps.

3. Install the protection layer of Geotextile membrane above the PVC membrane over the entire vertical area in full accordance with manufacturer's method statement

4. Secure top termination of waterproofing with continuous, PVC coated aluminium strip, and a suitable PU sealant from Colmef's joint sealant product range.

D. Seam Installation:

Hot air welding and end laps of overlapping sheets according to manufacturer's method statement to ensure a watertight seam installation. Inspect outside edge of seams with pointed metal probe and ensure completed laps lay flat and are free of voids, fish mouths, or wrinkles using one of the following methods:

1. Method 1: All seams of installed waterproofing can be subject to pneumatic test at test pressure of 2.00 bars.

2. Method 2: Testing the welded joint using a vacuum test machine

E. Any hole, resulting from construction activities, noted in installed membrane shall be repaired in accordance with manufacturer's method statement.

Corner Joint Installation

A. Install corner details in according to waterproofing manufacturer's written instructions.

1. Use the same welding technique as specified for membrane.

Ambient Temperature

+5°C - +60°C

Packaging

Roll size: 2.10 m (roll width) x 20m (roll length)

Unit weight: 2.16 kg/m²

Storage

Rolls shall be stored in their original package, in horizontal position and under cool and dry conditions protected from direct sunlight and rain.

Insuwrap PVC membrane does not expire and has a very long life expectancy.

Limitations

- Do not directly apply the PVC membrane permanently on bitumen and plastics other than PVC, a separation layer of geotextile is required.
- The PVC membrane can be exposed to temporary UV light for a period of 6 months
- Insuwrap 2000 TNL-FB can be exposed temporary to ground water or polluted water with temperature up to 50°C for 3 months.

Health & Safety

Local safety regulations must be observed. Information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Colmef Insuwrap products, are given in good faith based on Colmef current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Colmef's recommendations.

The information in this Technical Data Sheet is based on Colmef Monneli's experience. Colmef Monneli does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Colmef Monneli's Data Sheets are updated on regular basis. It is the user's responsibility to obtain the latest version.

DUBAI
ABU DHABI
ITALY

P.O. Box 123808 Dubai UAE
P.O. Box 127326 Abu Dhabi, UAE
Z.I. Ponte d'Ássi 06024 Gubbio (PG)

T. +971 4 8803488 F. +971 4 8803450
T. +971 2 5511949 F. +971 2 5511749
T. +39 75 9221297 F. +39 75 9221174

INSUWRAP 2000 TNL-FB

Technical Data Sheet
Edition: February 2023
Revision: 02

colmef@colmef.ae

www.colmef-me.com