

MONNELI INSUWRAP 1200 WM

1.2 mm thick with Fleeceback PVC Membrane for Covered Roofing System

Product Description

Insuwrap 1200 WM is a homogeneous PVC (polyvinylchloride) sheet waterproofing membrane with polyester mesh.

Properties

Appearance: PVC rolled sheet membrane

Membrane Thickness: 1.20mm

Colour: Grey

Uses

Waterproofing of Covered Roofs and Podiums

Advantages

- High tensile strength and elongation
- Hot air weldable
- Flexible throughout life span
- Resistant to ageing
- Long durability
- High dimensional stability
- Anti-Root membrane
- Can be installed on wet and dry substrates
- Designed to be used in hot climates
- Reaction to Fire - Class B
- Covered Application

Standards

- Tested according to testing requirements of ASTM D4434 and DIN 16735.

Complimentary Products

- PVC Coated Aluminium sheet for termination
- Geotextile membrane
- Protection layer
- PU Sealant
- Aluminium flashing
- Steel washers

Technical Data

Test Performed	Test Method	Results
Membrane Thickness	ASTM D 4434	1.2mm
Mass	DIN 16735	1.56 kg/m ²
Tensile Strength	DIN 16735 Min 8.0 N/mm ²	≥11.0 N/mm ²
Elongation at Break	DIN 16735 Min 150%	>300%
Thermal Stability	DIN 16735 Less than 1% (6 hrs - 90°C)	<0.3%
Tear Strength	Min 80 N	> 95N
Seam Strength	ASTM D 4434	>82 N
Tear Resistance	ASTM D 4434	>95 N
Puncture Resistance	DIN 16735 Drop hammer 500 grams, from 300mm no leak	Passed
Water Vapour Diffusion Resistance	DIN 16735 Less than 30,000	<23,000 μ
Cold Bend	DIN 16735 No cracks at -20°C	No cracks at -30°C
Resistance to Algae & Rot		High resistance

Instruction for Use

Substrate Preparation

The surface of the sloping concrete shall be sound, clean, dry or wet, and uncontaminated. This preparation shall be as such as to leave a sound exposed concrete surface free from dust, laitance and any delirious matter.

Application

LOOSELY LAID PVC SHEET INSTALLATION

Install loosely laid PVC sheets over entire roof area so the light colour is at the visible side towards the substrate.

A. Horizontal Installation:

1. Install the separation layer over the entire horizontal area before the PVC membrane (if needed) in full accordance with Colmef's method statement
2. Accurately align sheets and maintain uniform side and end laps of minimum dimensions required. Stagger end laps.
3. Install the Geotextile membrane as a separation layer above the PVC membrane followed by a minimum of 50mm extruded polystyrene thermal insulation
4. As much as practically possible the joints will not be against the direction of flow.

B. Upstands:

1. Apply the **1200 WM** membrane directly on the concrete up-stand with Neofil S10 contact adhesive
2. Secure top termination of waterproofing with continuous, Aluminum flashing strip, and Elastoseal PU25, a Polyurethane sealant from Colmef.

C. Seam Installation: Hot air welding and end laps of overlapping sheets according to manufacturer's method statement to ensure a watertight seam installation. Inspect outside edge of seams with pointed metal probe and ensure completed laps lay flat through one of the following methods:

1. Method 1: All seams of installed waterproofing can be subject to pneumatic test at test pressure of 2.00 bars.
2. Method 2: Testing the welded joint using a vacuum test machine

D. Any hole, resulting from construction activities, noted in installed membrane shall be repaired in accordance with manufacturer's method statement.

CORNER JOINT INSTALLATION

A. Install corner details in accordance to waterproofing manufacturer's written instructions.

1. Use same welding system as specified for membrane.

Ambient Temperature

+5°C - +60°C

Packaging

Roll size: 2.10 m (roll width) x 20m (roll length)

Unit weight: 1.56 kg/m²

Storage

Rolls shall be stored in their original package, in horizontal position and under cool and dry conditions protected from direct sunlight and rain.

Insuwrap PVC membrane does not expire and has a very long life expectancy.

Limitations

- Do not directly apply the PVC membrane permanently on bitumen and plastics other than PVC, a separation layer of geotextile is required.
- The PVC membrane can be exposed to temporary UV light for a period of 6 months.
- **Insuwrap 1200 WM** can be exposed temporary to ground water or polluted water with temperature up to 50°C for 3 months.

Health & Safety

Local safety regulations must be observed. Information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Colmef Insuwrap products, are given in good faith based on Colmef current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Colmef's recommendations.

The information in this Technical Data Sheet is based on Colmef Monnelli's experience. Colmef Monnelli does not accept any liability arising from the use of its products as it has no direct or continuous control over where or how its products are applied. All Colmef Monnelli's Data Sheets are updated on regular basis. It is the user's responsibility to obtain the latest version.

DUBAI
ABU DHABI
ITALY

P.O. Box 123808 Dubai UAE
P.O. Box 127326 Abu Dhabi, UAE
Z.I. Ponte d'Ássi 06024 Gubbio (PG)

T. +971 4 8803488 F. +971 4 8803450
T. +971 2 5511949 F. +971 2 5511749
T. +39 75 9221297 F. +39 75 9221174

INSUWRAP 1200 WM
Technical Data Sheet
Edition: February 2023
Revision: 02

colmef@colmef.ae

www.colmef-me.com